

B2 Mg/m³ or more in the ordinary temperature molding and was about 7.40 Mg/m³ or more in the warm molding. In the compacts, defects such as flaws and fractures were not observed.

The properties of sectional microstructure of the compact were normal, and no coarse cavities were observed.


Page 25, lines 11-16, delete current paragraph and insert therefor:

B3 Regarding the Comparative Examples outside of the scope of the invention, the ejection forces were as high as more than 20 MPa, the densities in the ordinary temperature molding were as low as 7.25 Mg/m³ or less, the densities in the warm molding were as low as 7.35 Mg/m³ or less, flaws were observed on the surfaces of the compacts, or coarse cavities were observed in the vicinity of the surfaces of the cross sections of the compacts.

REMARKS

Claims 1-7 are pending. By this Supplemental Preliminary Amendment, the specification is amended for editorial reasons to eliminate some inadvertent underlining that was introduced into the Amendment. No new matter has been added. Prompt and favorable examination on the merits is respectfully solicited.

Respectfully submitted,



James A. Oliff
Registration No. 27,075

Joel S. Armstrong
Registration No. 36,430

JAO:JSA/slm

Date: February 15, 2002

OLIFF & BERRIDGE, PLC
P.O. Box 19928
Alexandria, Virginia 22320
Telephone: (703) 836-6400

DEPOSIT ACCOUNT USE AUTHORIZATION Please grant any extension necessary for entry; Charge any fee due to our Deposit Account No. 15-0461
--